

AR-97



Polymeric color	White glossy
Coating type	Epoxy phenolic
Main application	Production/Injection tubing, flowlines, line pipe
Polymeric thickness	140 - 350 microns (5.6 - 14 mils)
Protection against H2S, ppm (mol.)	10000
Protection against sweet corrosion (CO2), ppm (mol.)	20000
Protection against ARPD	extra high
Coupling's intermetallic protection	v
Coating Roughness, microns	2
Acid/Alkiline treatments	Acid treatments: 10% HCl, t=50°C, max.duration 24 hours Alkaline treatments: 10% NaOH, t=50°C, max. duration: 24 hours
Polymeric temperature, up to	302°F (150°C)**
Short-time polymeric temperature, not more than / Including steam treatments	392°F (200°C)
Intermetallic temperature, not less than	
Polymeric layer adhesion, not less than	12MPa
**Temperature clarification	266°F (130°C) - severe CO2 corrosion; 266°F (90°C) - severe H2S corrosion

ALTERIVER

Flow. Naturally

Alteriver inc.

1111 Katy Fwy Ste 910,
Houston, TX 77079
info@alteriver.com
alteriver.com

Types of Protection:

ARPD

Alteriver's AR-97 coating is an epoxyphenolic polymer based protective system with enhanced temperature resistance, designed to protect tubing in environments with excessive asphaltene-resin-paraffin deposits (ARPD) and mild corrosion.